

DEVELOPER FOR PHOTSENSITIVE POLYIMIDE PRECURSOR AND METHOD FOR RECOVERING SAME

Patent number: JP2000305280
Publication date: 2000-11-02
Inventor: FUJIMOTO KOJI; YOSHIMURA TOSHIO
Applicant: TORAY INDUSTRIES
Classification:
- international: G03F7/32; C08F2/44; C08F2/48; C08G73/10; C08K5/00; C08K5/17; C08L79/08; G03F7/027; G03F7/028; G03F7/037; H01L21/027
- european:
Application number: JP19990110593 19990419
Priority number(s): JP19990110593 19990419

Report a data error here

Abstract of JP2000305280

PROBLEM TO BE SOLVED: To provide a developer for a photosensitive polyimide precursor having no danger of ignition in a developing step and safely usable in an apparatus not protected from explosion by using specified proportions of a bipolar aprotic polar solvent, an ester and water as components. **SOLUTION:** The developer consists of 60-80 wt.% bipolar aprotic polar solvent, 10-30 wt.% ester and 10-30 wt.% water. The bipolar aprotic polar solvent is, e.g. N-methylpyrrolidone, N,N-dimethylacetamide, N,N-dimethylformamide or N,N-diethylformamide. The ester is, e.g. ethylene carbonate, propylene carbonate, ethyl lactate, ethyl pyruvate or propylene glycol monomethyl ether acetate. A mixture of two or more such esters may be used. The water is preferably pure water such as ion-exchanged water or distilled water.

Data supplied from the **esp@cenet** database - Worldwide